Amendments to the Claims:

This listing of the claims will replace all prior versions, and listings, of claims in the application:

Listing of the claims:

Claim 1 (canceled)

Claim 2 (currently amended) Composition according to claim [[1]] Z, characterized in that it contains the flow agent in a quantity of less than or equal to 3% by weight.

Claim 3 (currently amended) Composition according to claim [[1]] Z, characterized in that the mineral solid flow agent has a particle size greater than 125 µm.

Claim 4 (canceled)

Claim 5 (previously presented) Powdery composition which includes as a first component a calcic compound complying with formula I

$$xCaA.(1-x)[yMgA+(1-y)MgO],$$
 (I)

in which

A is a =(OH)₂ or =CO₃ group, and

x and y are molar fractions where $0 \le x \le 1$ and $0 \le y \le 1$,

and which includes as a second component in the powdery composition a quantity of a mineral solid flow agent in the form of particles having a size greater than $90 \, \mu m$, said quantity of mineral solid flow agent being greater than zero and less than 5% by weight of the powdery composition;

wherein the calcic compound which is included as the first component of the powdery composition has a particle size less than 250 um; and

characterized in that the mineral solid flow agent is attapulgite.

Claim 6 (currently amended) Composition according to claim 1, Powdery composition which includes as a first component a calcic compound complying with formula I

xCaA.(1-x)[vMgA+(1-v)MgO], (I)

in which

A is a =(OH), group, and

x and y are molar fractions where 0 < x < 1 and 0 < y < 1,

and which includes as a second component in the powdery composition a quantity of a mineral solid flow agent selected from the group consisting of vermiculite, perlite, diatomaceous earth and silica, in the form of particles having a size greater than 90 µm, said quantity of mineral solid flow agent being greater than zero and less than 5% by weight of the powdery composition;

wherein the calcic compound which is included as the first component of the powdery composition has a particle size less than 250 µm; and

characterized in that the mineral solid flow agent is raw vermiculite.

Claim 7 (currently amended) Composition according to claim 1; Powdery composition which includes as a first component a calcic compound complying with formula I

xCaA.(1-x)[yMgA+(1-y)MgO], (I)

in which

A is a =(OH), group, and

x and y are molar fractions where $0 \le x \le 1$ and $0 \le y \le 1$,

and which includes as a second component in the powdery composition a quantity of a mineral solid flow agent selected from the group consisting of vermiculite, perlite, diatomaceous earth and silica, in the form of particles having a size greater than 90 µm, said quantity of mineral solid flow agent being greater than zero and less than 5% by weight of the powdery composition:

wherein the calcic compound which is included as the first component of the powdery composition has a particle size less than 250 µm; and

characterized in that the mineral solid flow agent is expanded vermiculite.

Claim 8 (currently amended) Composition according to claim 1, Powdery composition which includes as a first component a calcic compound complying with formula I

xCaA.(1-x)[yMgA+(1-y)MgO]. (I

in which

A is a =(OH), group, and

x and y are molar fractions where $0 \le x \le 1$ and $0 \le y \le 1$,

and which includes as a second component in the powdery composition a quantity of a mineral solid flow agent selected from the group consisting of vermiculite, perlite, diatomaceous earth and silica, in the form of particles having a size greater than 90 µm, said quantity of mineral solid flow agent being greater than zero and less than 5% by weight of the powdery composition;

-4-

Document #: 45276

wherein the calcic compound which is included as the first component of the powdery composition has a particle size less than 250 µm; and

characterized in that the mineral solid flow agent is expanded perlite.

Claim 9 (currently amended) Composition according to claim [[1]] Z, characterized in that the calcic compound is at a degree of purity greater than 90%.

Claim 10 (currently amended) Composition according to claim [[1]] Z, characterized in that the calcic compound which makes up a first component of the powdery composition has a particle size of less than $20 \mu m$.

Claim 11 (previously presented): Powdery composition which includes as a first component a calcic compound complying with formula I

$$xCaA.(1-x)[yMgA+(1-y)MgO],$$
 (I)

in which

A is a = $(OH)_2$ or = CO_3 group, and x and y are molar fractions where 0 < x < 1 and 0 < y < 1,

and which includes as a second component in the powdery composition a quantity of a mineral solid flow agent in the form of particles having a size greater than $90 \, \mu m$, said quantity of mineral solid flow agent being greater than zero and less than 5% by weight of the powdery composition;

wherein the calcic compound which is included as the first component of the powdery composition has a particle size less than $250 \, \mu m$; and

characterized in that the mineral solid flow agent is raw vermiculite.

Claim 12 (previously presented): Powdery composition which includes as a first component a calcic compound complying with formula I

$$xCaA.(1-x)[yMgA+(1-y)MgO],$$
 (I)

in which

A is a = $(OH)_2$ or = CO_3 group, and x and y are molar fractions where $0 \le x \le 1$ and $0 \le y \le 1$.

and which includes as a second component in the powdery composition a quantity of a mineral solid flow agent in the form of particles having a size greater than 90 μm , said quantity of mineral solid flow agent being greater than zero and less than 5% by weight of the powdery composition;

wherein the calcic compound which is included as the first component of the powdery composition has a particle size less than $250\,\mu m$; and

characterized in that the mineral solid flow agent is expanded vermiculite.